

HA, P-S and Film Adhesive Application Comparisons

Board	Types of Art											Digitals								Board Info																							
This chart is a combination of manufacturers suggestions AND the result of tested mounting results BETWEEN 2006-2008. Updated, new release and 2011 products may not match the results in this test. Copyright © Chris A. Paschke, CPF GCF, April 11	Lightweight Porous Paper	Coated Paper-mechanical	Coated Paper-vacuum	Heavy or Textured Papers	Asian Papers	Watercolors	Original Graphic	Polyester Encapsulate	RC Photo-mechanical	RC Photo-vacuum	RA-4 Photographs	Fabrics / Textiles	Raw Canvas	Digital Canvas	Electrographic Copy	Electrostatic / Laser Copy	Dye Sublimation	Thermal Transfer	Thermal (dye) Inkjet	Thermal (pigment) Inkjet	Piezo Inkjet	Digital Canvas	Time - after draw (actual)	Temperature	Permanent	Removable	Reversible / Preservation	Cure or Cool under weight	Neutral Ph or stable & inert	Orange peel						Rollers	Mechanical	Hot Vacuum					
															N	N			N																								
Heat Activated (HA) Boards																																											
Bainbridge Artcare Restore	X				X	x	X	X	X	X	X													15s-1m	F150-170			X	X	X									X	X			
SpeedMount	X	X	X						X	X	X													1-3m	F150-160		X	X											X	X			
Heat Activated Foam-HAF	X	X	X	X	X			X	X	X	X	X	X	X		X	X		X	X	X	X		1-3m	F160-180		X	X												X	X		
Bienfang Single Step	X	X	X	X	X				X	X	X	X	X	X		X	X			X	X	X		2-3m	F180	X													X	X			
Step 150	X	X	X	X	X			X	X	X	X	X	X	X		X	X		X	X	X	X		15s-3m	F150	X		X											X	X			
Alcan/IP HA Fome-Cor	X	X	X	X	X			X	X	X	X	X	X	X		X	X		X	X	X	X		1.5-3m	F170-180	X													X	X			
Gilman InSite Heat-Activated Foamboard	X	X	X	X	X			X	X	X	X					X	X		X	X	X	X		15s-1m	F160	X			X										X	X			
Hartman HartMount	X	X	x		X				X	X	X					X	X		X		X			1-3m	F185	X													X	X			
Savage NuCor Heat Activated Foam	X	X		X					X	X	X					X	X		X		X			20s-1m	F180		X		X										X	X			
Filmtax ProCore Heavy Wt	X	X		X												X	X		X		X			30s-1m	F200	X				X	X								X	X			
Kool Tack Preserve Foamboard	X	X	X			x	X		X	X	X									x				15s-30s	F150-160			X	X	X	x								X	X			
Drymount Foamboard Archival	X	x	x	x	x				X	X	X		x	x	x				x	X	x	X		15s-1m	F150-160		X	X			x								X	X			
Drymount Foamboard - white	X	X	X	X	X				X	X	X		x	x					X	X	X	X		15s-45s	F150-160		X	X												X	X		
Adhesive Dry Mount Films/Tissues																																											
Expression Fusion 4000	X	X	X	X	X				X	X	X		x	X						X	X	X		2-3m	F190-200		X		X	X										X	X		
RagMount (ClearMount)	X	X	X	X	X				X	X	X		x	X			X	X		X	X	X		2-3m	F180	X		X	X											X	X		
Drytac FloBond	X	X	X	X	X				X	X	X		x	X			X	X		X	X	X		2-3m	F180-200		X		X	X											X	X	
GicleeMount	X	X	X	X	X				X	X	X		x	X						X	X	X		2-3m	F190-225	X		X													X	X	
Pressure-Sensitive (P-S) Boards		NA	NA				NA	NA	NA	NA														NA	NA																		
Alcan Self Adhesive Fome-Cor LT	X															X	X	X	X	X								X		X	X									X			
Bainbridge SA Foamboard	X						X			X		X	X			X	X	X	X	X	X	X						X		X										X			
Crescent PerfectMount Board X	X									X						X	X		X	X	X							X		X	X									X			
PerfectMount Foam	X									X						X	X	X	X	X	X	X						X		X											X		
Drytac PS Gatorfoam	X			X	X				X		X	X	X	X		X	X	X	X	X	X	X						X		X											X		
Foam Board	X			X	X				X		X	X	X	X		X	X	X	X	X	X	X						X		X											X		
Elmer's Quick Stick HT Self Adhesive	X			X	X				X		X	X	X	X		X	X	X	X	X	X	X						X		X											X		
Gilman High Tack Foam	X									X						X	X	X	X	X	X	X						X		X	X										X		
Hartman HarTac	X			X	X											X	X	X	X	X	X	X						X		X											X		
Pressure-Sensitive (P-S) Films																										NA	NA																
3M PMA	X															X	X	X	X	X	X	X						X			X										X		
Crescent PerfectMount Film	X			X																								X		X											X		
Neschen Gudy 870	X			X	X					X						X	X	X	X	X	X	X						X			X										X		
Neschen Gudy 831	X			X	X				X							X	X	X	X	X	X	X						X			X										X		
Drytac Media-Tac with Roller Laminator	X			X	X					X			X	X		X	X	X	X	X	X	X						X													X		

Legend: NA = nor applicable; x = moderate bond; X = good bond; X = excellent bond and tear strength; N = do not apply heat

Copyright © Chris A. Paschke, CPF GCF, updated April 11